



K0244
North America
11/6/2009

KRATON[®] D1101 K Polymer

Data Document

Identifier : K245DDI10U

Description

Kraton D1101 K is a clear, linear triblock copolymer based on styrene and butadiene with a polystyrene content of 31%. It is supplied from North America in the physical form identified below.

- Kraton D1101 KT - supplied as a dusted porous pellet
- Kraton D1101 KU - supplied as an undusted porous pellet
- Kraton D1101 KIM - supplied as a dusted powder

Kraton D1101 K is used as a modifier of bitumen or thermoplastics and in compound formulations. It may also find use as an ingredient in formulating adhesives, sealants and coatings.

Sales Specifications

Property	Test Method	Units	Sales Specification Range	Notes
Polystyrene Content	KM 03	%m	29.0 33.0	
Antioxidant	KM 08	%m	0.15 TO 0.40	b
Total Extractables	KM 05	%m	\leq 1.0	
Volatile Matter	KM 04	%m	\leq 0.7	
Ash, KT	BAM 908	%w	0.15 TO 0.35	a
Ash, KIM	BAM 908	%w	4 TO 6	c

a Talc

b Non-staining phenolic antioxidant

c The final dusting level is a combination of the talc from the original D1101 KT plus calcium carbonate added during the milling process.

Typical Properties (These are typical values and may not routinely be measured on finished product)

Property	Test Method	Units	Typical Value	Notes
Specific gravity	ASTM D4025	gm/cc	0.94	
Hardness	ASTM 2240	Shore A (10s)	69	d
Styrene / Rubber ratio	n/a		31/69	
Tensile strength	ASTM D-412	psi	4600	e
Melt Index 200°C, 5kg	n/a	gms/10 Min.	\leq 1	
Elongation at break	ASTM D-412	%	880	e
Solution Viscosity	BAM 922	cps	3900	c
Diblock content	n/a		16	
300% Modulus	ASTM D-412	psi	400	e

c 25%w toluene solution at 25°C

d Typical values on polymer compression molded at 350°F

e Measured on films cast from a solution in toluene

Packaging

Kraton Polymers are available in a number of different package types. For information specific to this grade, please contact your local Kraton Polymers representative.

(R) KRATON and the KRATON logo are trademarks owned by the KRATON Polymers Group of Companies

End Use Requirements

If the finished article is intended for use in food contact and packaging applications, toys, or human contact areas, manufacturers of the final product should observe all relevant regulations. Some of these regulations require tests to be carried out on the final product, e.g. migration. These are the responsibility of the final product manufacturer. Information on the food packaging clearances of individual products is available from Kraton Polymers.

Cosmetics, Drugs and Medical Device Policy

No customer of Kraton Polymers LLC and/or any of its direct or indirect subsidiaries ("Kraton Polymers"), or any other party, shall, without the express written consent of Kraton Polymers for each specific, individual application, be permitted to manufacture, use, sell, process, or otherwise supply, directly or indirectly, any Kraton Polymers Product, or any compound containing or made from any Kraton Polymers Product, in any of the following applications:

- 1. Cosmetics (exclusive of packaging or delivery applications);
- 2. Drugs and other Pharmaceuticals (exclusive of packaging or delivery applications);
- and
- 3. Medical devices; provided, that any medical device that satisfies any one of the following definitions shall not be deemed to fall within the foregoing medical device restriction: (a) any medical device falling within the definition of either a Class I or Class II medical device, as defined in any federal law or regulation of the United States or Canada, or (b) any medical device falling within the definition of a Class I or Class II(a) medical device, as defined by any applicable regulation of the European Union or any member state thereof.

No customer of Kraton Polymers, or any other party, shall be permitted to use any of Kraton Polymer's trade names, trademarks, logos or other similar identifying marks or characteristics for the manufacture, sale, or promotion of its cosmetics, drugs, pharmaceutical products/materials, or medical devices.

Safety and Handling Precautions

Read the Safety Data Sheet carefully and thoroughly before beginning any work. Additional information relating to the health, safety, storage, handling and processing of Kraton Polymers products can be found in "Health and Safety Aspects of Kraton D and Kraton G Polymers" (Document K0155), available from your local Sales Representative or the company website. Kraton Polymers also recommends that customers or users consult other sources of safety information, for example, the current edition of the "Code of Practice on the Toxicity and Safe Handling of Rubber Chemicals," British Rubber Manufacturers Association Limited. Kraton Polymers products and compounds can accumulate electrostatic charges when rubbed, chafed or abraded. Processing and storage equipment for use with Kraton Polymers products should provide a means of dissipating any charges that may develop.

When processing Kraton Polymers products, maintain a fire watch if the material reaches 225°C (437°F) for Kraton IR and Kraton D (polymers and compounds), and 280°C (536°F) for Kraton G (polymers and compounds). The temperatures listed above are indicated only for safety reasons (risk of fire and product degradation) and are not necessarily recommended for processing. Degradation of the polymer (polymer breakdown) will start at lower temperatures depending on the specific processing conditions. Therefore, operating below these temperatures does not guarantee the absence of product degradation.

Kraton Polymers products (the neat resin or the base product) are high molecular weight polymers which are non-toxic and biologically inactive.

Warranty

The information contained in this publication is, to the best of Kraton Polymers' knowledge, true and accurate, but any recommendations or suggestions that may be made are without guarantee, since the conditions of use and storage are beyond Kraton Polymers' control. The customer understands that it shall make its own assessment to determine the suitability of a Kraton Polymers product for a particular purpose. Further, nothing contained herein shall be construed as a recommendation to use any Kraton Polymers product in conflict with existing patents. All products purchased from or supplied by Kraton Polymers are subject to terms and conditions set out in the applicable contract, order acknowledgement and/or bill of lading. Kraton Polymers warrants only that its products will meet those specifications designated therein.

KRATON POLYMERS MAKES NO OTHER WARRANTY REGARDING ITS PRODUCT, EITHER EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE; OR THAT THE USE OF SUCH INFORMATION OR KRATON POLYMERS PRODUCT WILL NOT INFRINGE ANY PATENT.

For further information:		In Asia Pacific	
USA Tel (toll free):	+1-800-4-Kraton (+1 800-457-2866)	Tel Japan	+81-3-3769-5990
USA Tel:	+1-281-504-4950	Hong Kong	+852-250-80-657
USA Fax:	+1-281-504-4953	Taiwan	+886-2-2545-1538
In Europe / Africa		China	+86-21-6289-6161
Europe Fax:	+44-(0)1244 405 949	South East Asia / India	+91-11-2923-0324
In South America		Australia	+61-41-937-5055
Fax:	+55-(0)19-3874-7275	Or contact your local KRATON Polymers Representative	
		Visit us at www.kraton.com	
		Email info@kraton.com	